

EPOCH MASTER GLOBAL BUSINESS(JIANGSU)INC.

RM.3-93, TENGFEI BUILDING, NO.88 JIANGMIAO RD., RESEARCH AND INNOVATION PARK,

NANJING ZONE, (JIANGSU) PILOT FREE TRADE ZONE, CHINA

Dicalcium Phosphate Dihydrate

General Characteristics:

Product code: DCPD20-60(TAB) Formula: CaHPO $_4$ ·2H $_2$ O White powder

 Molecular weight:
 172.09

 Odor:
 Odorless

 CAS Number:
 [7789-77-7]

 EINECS No.:
 231-826-1

 INS:
 341(ii)

Solubility: Practically insoluble in water and in ethanol(96%). It dissolves

In dilute hydrochloric acid and in dilute nitric acid

Uses:

Calcium fortification food.

Aerated agent、Nutritional supplements.

Stability agent \ Toothpaste friction agent.

Packing and storage:

➤ 25kg/net paper bag and PE bags sealed inside.

- Store in a well-closed bag at room temperature, protect from light, moisture and pest infestation.
- ➤ Shelf life---two years

Microbiological Specification:

Total viable count 1000CFU/gr.max Yeast&Molds 50CFU/gr.max

E.Coli AbsentShigella AbsentS. aureus AbsentS.hemolyticus AbsentSalmonella Absent

GMO-Status:

The product is a non GMO product and is free from any recombinant DNA.

Irradiation/Radioactivity:

Yunbo's Dicalcium phosphate dihydrate was never subjected to any kind of ionized irradiation and contains no radioactivity not even in minor amounts.

BSE/TSE:

No raw materials from bovine origin are used nor are any bovine constituents present in the product.



EPOCH MASTER GLOBAL BUSINESS(JIANGSU)INC.

RM.3-93,TENGFEI BUILDING,NO.88 JIANGMIAO RD., RESEARCH AND INNOVATION PARK, NANJING ZONE,(JIANGSU) PILOT FREE TRADE ZONE ,CHINA

Specifications(BP/USP/E341(ii)/FCC):

Test Parameter	Ph.Eur	USP-NF	E341(ii)	FCC
Appearance	White or almost white	White or almost white	White or almost white	Occurs as a
	crystalline powder or	crystalline powder or	crystalline powder or	white powder
	colourless crystals	colourless crystals	colourless crystals	
Identification A	Passes test	Passes test	Passes test	Passes test
Identification B	Passes test	Passes test	Passes test	Passes test
Identification C	It complies with the			
	limits of the assay			
Assay	98.0%~105.0%	98.0%~105.0%	98.0%-102.0%	97.0%-105.0%
【Ca, asCaHPO ₄ 】	98.0% 103.0%			
P2O5			50.0-52.5%	
Loss on ignition	24.5%-26.5%	24.5%~26.5%	≤26.5%	24.5%-26.5%
Heavy metal(as Pb)		≤0.003%		
Mercury			≤1.0ppm	
Arsenic	≤10.0ppm	≤3.0ppm	≤1.0ppm	≤3.0ppm
Lead			≤1.0ppm	≤2.0ppm
Cadmium			≤1.0ppm	
Aluminium			≤100.0ppm	
Chloride	≤0.25%	≤0.25%		
Sulfate	≤0.5%	≤0.5%		
Acid-insoluble	≤0.2%	≤0.2%		
substances				
Carbonate	To pass the test	To pass the test		
Barium	To pass the test	To pass the test		
Limit of fluoride	≤100.0ppm	≤50.0ppm	≤50.0ppm	≤50.0ppm
Iron	≤400.0ppm			

Product Code	Granularity	Particle size(mesh/µm)
DCPD20-60(TAB)	Large particles	20-60 mesh

佰舸斯达国际贸易(江苏)有限公司 EPOCH MASTER GLOBAL BUSINESS (JIANGSU) INC.

IT RINGRO (1